



80 Cypress Street, Warwick, RI 02888 ♦ U.S.A.
401-941-3000 ♦ 800-272-7752 ♦ Fax: 1-401-941-0150
info@rbcepoxy.com ♦ www.rbcepoxy.com

♦ TECHNICAL BULLETIN ♦ TECHNICAL BULLETIN ♦ TECHNICAL BULLETIN ♦

WB-A-101 Repositionable Pressure Sensitive Adhesive

Description:

WB-A-101 is a waterbased, pressure sensitive adhesive which has been specially formulated for repeated applications and removals, allowing effective repositioning of substrates. The material is suitable for application on a wide variety of surfaces including: Paper, Corrugated, Fabric, Sealing Tapes and foam. Surfaces treated with WB-A-101 may be repositioned up to 5 times without losing adhesive strength or leaving behind a messy residue.

Application Methods:

- Spray
- Brush
- Rollcoat

Typical Bond Range:

1 mil. Film..... 2-5 minutes to tack (tack retention up to 30 days) @ 25 deg. C

Physical Properties:

Color.....	White Liquid
Viscosity @ 25 deg. C, #3 spindle @ 20rpm.....	1225 cps
Total Solids, % by weight.....	54.5 – 56.5
Ph.....	8.5 – 9.5
Dry Film Appearance.....	Clear/Tacky
Peel Strength, 180 degree peel, pli..... (30 minute dwell)	2.0 minimum

Storage: Store in closed container; 45-80 degrees F. Do not Freeze.

The manufacturer, RBC Industries, Inc., hereby gives notice that any statement or representation made by the manufacturer in the sales of any and all of its products shall not create any warranty of merchantability expressed or implied. Statements or descriptions are informational only and the purchaser shall be solely responsible for determining the adequacy of the product for any and all uses.